



Product Information

FELDER-Soldering Grease

Pasty soft soldering flux according to ISO 9454-1 - 3214

Art.-No.: 243100..

All information about our products are the result of our long standing experience which we would like to pass on to our customers as application support. However, as we do not have any influence on the application of the works carried out with our products, please see the warranty claims in our conditions of sale because our liability is limited.

This product information does not constitute warranted properties.

Application

Flux for soft soldering of copper and copper alloys in the copper tube installation, radiator construction, plumbing works, dip soldering, fittings manufacturing and other general solder works.

Properties

Chemical composition	:	On basics of zinc and ammonium chlorides in organic preparation
Description of standard	:	ISO 9454-1 – 3214 (EN 29454-1, 3.1.1.C)
Condition	:	pasty

Flux residues

The flux residues are corrosive and have to be removed with water or a suitable cleaning agent (possibly neutralization, ultrasound).

Delivery form

20	g	tins
50	g	tins
100	g	tins
250	g	tins
500	g	tins
1.000	g	tins

Other bottles sizes on request.

Storage advices

Store in tightly closed containers, protected against sunlight and moisture. Stored properly the product is durable at least 24 months.

Advices

Other fluxes according to the same and other ISO-codes are included in our standard delivery program. Please do not hesitate to contact us for further information.